



UNITED GILSONITE LABORATORIES

P.O. BOX 70 • SCRANTON, PA 18501-0070

Makers of DRYLOK® Masonry Waterproofer and ZAR® Wood Stains and Finishes

DRYLOK Clear Waterproofer Spray Specification D-99 November 2013

For best results **DRYLOK Clear Waterproofer** should be well stirred and sprayed at room temperature (70°F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Gas Powered Option: GMAX II 5900 or Larger

- Standard (Hi-Boy – P/N 248688/ Lo-Boy P/N 248687)
- Premium (Hi-Boy – P/N 258732/ Lo-Boy P/N 258737)

Electric Powered Option: Ultra Max II 1596 or larger

- Standard Hi-Boy P/N 258764
- Premium Hi-Boy P/N 2578763

Spray this material with a tip size of .031-.035 tip.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.