



Spray Specifications – DRYLOK® EXTREME Waterproofer

For best results DRYLOK® Extreme waterproofer should be well stirred and sprayed at room temperature (70°F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Graco Ultra Max II PC Pro 490, 495, or 595 Electric Airless Sprayers

Please read all of Graco safety, assembly and process instructions for your sprayer before using. Never point gun at yourself or others. Contact Graco for any questions on operation and use.

General Instructions:

Remove Gun and Hose (manifold) filters prior to spraying. Use Graco RAC X spray tip sizes anywhere from 0.025 to 0.035 inches. Spray pressure 2200 to 2500 psi; pressure may be adjusted for sprayer type and tip size. Hold gun twelve inches from surface when spraying. Spray cross hatching patterns (North/South then East/West) with two coats building to a 14 to 16 wet mil thickness. First coat, back roll with ¾" nap or back brush to fill any pinholes or pores in masonry. Allow to dry 4 hours before applying second coat. Repeat first coat procedure.

Last Revision - March 2018

P.O. BOX 70 ■ SCRANTON, PA 18501-0070 ■ Phone 570-344-1202 ■ Toll Free 800-UGL-LABS ■ Fax 570-969-7634
Midwest Division - Jacksonville, IL 62650 ■ Western Division - Dayton, NV 89403 ■ Southern Division - Jackson, MS 39213

www.ugl.com